

---

---

## Technical Data Sheet

<b>FORTIS COAT526 GLOSS</b> <b>2 PART WATER BASED POLYURETHANE</b>
---

<b>DESCRIPTION</b>	A two component, medium solids, clear, gloss, water based polyurethane coating for brush or roller application.
<b>USES</b>	Fortis Coat526 Gloss is developed for use as a high performance clear polyurethane finish coat for timber and concrete substrates.
<b>FEATURES</b>	A medium build, 2 pack water-based non- yellowing polyurethane system with low odour during installation and excellent wear and abrasion resistance.
<b>COLOUR</b>	Clear gloss
<b>PACK SIZE:</b>	5lt kit. Larger kits made to order.
<b>SURFACE PREPARATION</b>	Substrates need to be clean, sanded, and dust and defect free.
<b>PRIMING</b>	Substrates should be primed with either FORTIS PRIME520C for concrete surfaces or FORTIS PRIME520W for timber surfaces. For more detail, please refer to their respective datasheets. Very dense or diamond ground exposed aggregate concrete may need to be primed with Polyurethane Adhesion Promoter. For all other substrates, please contact Fortis Adhesive & Coatings.
<b>MIXING</b>	Thoroughly mix the Part A and Part B components separately before application. Avoid entrapment of air. Use a Squirrel Mixer® (1 gallon size) with a variable speed drill, according to the manufacturers recommendations. Add the hardener slowly into the mixing vortex in the resin component maintaining the stirring throughout the addition. Continue for a minimum of three minutes. Use a clean straight edged stirring stick to bring the boundary layer on the sides and bottom of the resin container into the mix. Filter before use. Proper mixing of the viscous hardener into the low viscosity resin component is critical to achieve proper coating properties.
<b>APPLICATION</b>	Use a clean mohair roller or applicator bar and apply at a spreading rate of 12-15 m <sup>2</sup> per litre per coat.

---

## TECHNICAL DATA

<b>Composition:</b>	Aliphatic polyurethane
<b>Mix Ratio:</b>	4.5:1 Part A: Part B by weight or volume
<b>Film Thickness:</b>	35 microns per coat DFT
<b>Coverage Rate:</b>	12-15 m <sup>2</sup> per litre per coat
<b>Dry Time(Dust Free):</b>	Approximately 2 hours @ 20°C
<b>Recoat Time:</b>	12-24 hours in adequate drying conditions
<b>Top coating:</b>	Recoat within one day
<b>Final Cure:</b>	7 days
<b>Shelf Life:</b>	6 months in unopened container
<b>Clean Up:</b>	Water

## SAFETY DATA

Please refer to Fortis Safety Data Sheet for Fortis COAT526. Fortis COAT526 is safe if good working practices and proper application equipment is used. Caution should be taken as the material contains isocyanates. When sprayed this product may be harmful by inhalation. Good industrial hygiene should be observed at all times. Wear suitable protective clothing, impervious gloves, eye and face protection, including suitable breathing protection, such as an air-supplied respirator or organic canister mask. Avoid contact with exposed skin.

**Note:** *Fortis COAT526 contains isocyanates. It is recommended that positive air-supplied full-face respirator be used if spraying.*

### Disclaimer

*Fortis products should be used in accordance with the information contained here. Each user should read and consider this information carefully in the context of how the products will be handled and used in the workplace including in conjunction with other products. While the information contained here is to the best of our knowledge at the date of publication, Fortis makes no representation about the accuracy of the information. If you need clarification or more information, you should contact Fortis Adhesives & Coatings office directly. Fortis products are sold without express or implied warranties, other than as provided by statute, and subject to our standard terms and conditions (provided to customers and available on request). Subject to our standard terms and conditions, and any statutory provisions, Fortis accepts no responsibility (including in negligence) for loss or damage of any nature resulting from the use of Fortis Adhesives & Coatings products or reliance upon the information contained here.*